



PRODUCT DATA SHEET

07WS047 Drew Cryl High Performance Acrylic DTM Enamel

PRODUCT DESCRIPTION:

Economical, direct to metal fast drying styrenated acrylic that offers good color and gloss retention. Excellent adhesion to masonry and steel substrates.

INTENDED USES:

Recommended as top coat for all types of industrial structures, OEM, and heavy equipment.

PHYSICAL PROPERTIES:

Vehicle Type:	Acrylic
Color:	White and Custom Colors
Finish:	Low Sheen, Semigloss and Gloss
Solids	
By Volume:	34% Avg.
By Weight:	50% Avg.
Viscosity:	95-105 Krebs Unit
V.O.C.	0.85 lbs. per gal / 102 grams per litre
Recommended Dry Film Thickness:	1.5 – 2.0 mils
Theoretical Coverage:	368-480 sq.ft. per gal.

DRY TIME @ 77°F

Tack Free	25 min.
Handle	25 min.
Recoat	Anytime

NOTE:

Acrylic Industrial Latex
07 SERIES

SURFACE PREPARATION:

Surfaces that are to be coated must be clean, dry and free of surface contaminants.

MIXING:

Single component product, stir thoroughly before applying.

APPLICATION:

Airless – recommended tip sizes (.015-.022)
Air Assisted Airless – Kremlin Model 17:35 or larger, MX Gun
Conventional – Binks Model 2001 or equivalent
HVLP – Binks Model Mach 1
Brush/Roll – As needed.

PRIMERS:

None required

CLEANING UP:

Warm water if wet, ketones if dry.

ORDERING:

These products are available in 1 and 5 gallons pails, and 55-gallon drums.

COMPLIANCE: Federal Regulations

RULE	CATEGORY	MAXIMUM LEVELS	COMPLIANT
NESHAP	General	340 g/l	Yes
Automobile Refinishing	Single Stage Top Coat	600 g/l	Yes
AIM	Industrial Maintenance	450 g/l	Yes

SAFETY:

Products are intended for industrial use only, improper handling and misuse may be hazardous.
Please refer to the Material Safety Data Sheets for more detail safety information.

NOTE:

This information is based on technical data that we believe to be accurate and reliable and is intended to be used by persons having the knowledge and skill to apply these coating properly. We assume no responsibility for results or damages incurred from their use by the Buyer in whole or in part.

Main Office:

P.O. Box 29139,
Portland, OR 97296-9139
PH. 503-227-6427 FAX 503-227-1609
TOLL FREE 800-924-7874
www.drewpaints.com



Date: Mar. 2018

WATER-BASED SECTION

Acrylic Industrial Latex
07 SERIES