



# PRODUCT DATA SHEET

## 09 XT Series Temp-Line Track Marking Paint

### PRODUCT DESCRIPTION:

Water based air dry, temporary marking paint (Liquid Chalk) for road racing circuits. Temp-Line XT has been specifically engineered to allow you to temporarily mark your racing surface as required and then remove the paint from the road surface only using standard pressure washing.

### INTENDED USES:

Highly visible, temporary track marking paint for asphalt and concrete roadway, pit lane markings and road surface advertising.

### PHYSICAL PROPERTIES:

Vehicle Type:	PVA Resin
Color:	White and made to order (MTO)
Finish:	Flat
Solids	
By Volume:	24% Avg. (+/-2%)
By Weight:	42% Avg.
Viscosity:	90-94 ku
V.O.C.	116 grams per litre avg.
Pot Life	N/A
Recommended Dry Film Thickness:	2-3 mils
Theoretical Coverage:	130-192 sq.ft. per gal.(smooth surface) 390-576 ln.ft. per gal (4" stripe )

### DRY TIME @ 77° F

Tack Free	30-45 mins.
Return to Service	2 hour
Recoat	Infinite

NOTE: Temp-Line XT will soften when exposed to water; this paint is not intended to be used on curbing or high traffic areas.

## 09 XT Series

### **SURFACE PREPARATION:**

Surfaces that are to be coated must be clean, dry and free of surface contaminants. For best performance, pressure wash areas that are to be coated with a minimum of 1500psi water pressure.

---

### **THINNING: Use only clean water.**

Brush/Roll – Not recommended.

Airless and Conventional – Reduce up to 5%.

---

### **APPLICATION:**

Airless – Graco Linelazer line stripper or similar

Conventional Pressure feed line striper

Brush/Roll

---

### **CLEANING UP:**

Water

---

### **Coating Removal:**

Power wash with a minimum of 1500psi water pressure to remove paint from road surface.

---

### **ORDERING:**

These products are available in 5 gallons pails

---

### **SAFETY:**

Products are intended for industrial use only, improper handling and misuse may be hazardous. Please refer to the Material Safety Data Sheets for more detail safety information.

---

### **NOTE:**

This information is based on technical data that we believe to be accurate and reliable and is intended to be used by persons having the knowledge and skill to apply these coating properly. We assume no responsibility for results or damages incurred from their use by the Buyer in whole or in part.

### **Main Office:**

P.O. Box 29139,  
Portland, OR 97296-9139  
PH. 503-227-6427 FAX 503-227-1609  
TOLL FREE 800-924-7874  
[www.drewpaints.com](http://www.drewpaints.com)

